

U.S.S.N. 09/760,046

Filed: January 12, 2001

CLEAN VERSION OF AMENDMENTS PURSUANT TO 37 C.F.R. § 1.121(c)(1)(ii)

## Clean Version of Amended Claims

## Pursuant to 37 C.F.R. § 1.121(c)(1)(ii)

- Sub E  
C1
1. (Twice Amended) A method for making dry, micronized particles of an agent, comprising:
- (a) dissolving a macromolecular material in an effective amount of a solvent, to form a solution;
  - (b) dissolving or dispersing the agent in the solution to form an emulsion and thereby micronize the particles of the agent;
  - (c) freezing the mixture;
  - (d) drying by vacuum the mixture to form solid micronized particles of the agent dispersed in solid macromolecular material; and
  - (e) separating the solid micronized particles of agent from the macromolecular material.
3. (Amended) The method of claim 1 further comprising encapsulating the solid particles of agent in an encapsulating material.
4. (Amended) The method of claim 1 wherein greater than 90% solid particles are less than 0.2  $\mu\text{m}$  in diameter.
6. (Amended) The method of claim 1 wherein greater than 90% of the solid particles are between 10 nm and 1  $\mu\text{m}$  in diameter.
7. The method of claim 1 wherein the agent is a bioactive agent.
8. The method of claim 7 wherein the bioactive agent is a protein.
9. The method of claim 8 wherein the protein is a growth hormone.

ATLI #553973v1

U.S.S.N. 09/760,046

Filed: January 12, 2001

CLEAN VERSION OF AMENDMENTS PURSUANT TO 37 C.F.R. § 1.121(c)(1)(ii)

10. The method of claim 8 wherein the protein is an osteoprotegerin.
11. The method of claim 7 wherein the agent is selected from the group consisting of peptides, antibiotics, nucleotide molecules, and synthetic drugs.
12. The method of claim 1 wherein the macromolecular material is a polymer.
13. The method of claim 12 wherein the polymer is selected from the group consisting of polymers of lactic acid and glycolic acid, polyanhydrides, poly(ortho)esters, polyurethanes, poly(butic acid), poly(valeric acid), poly(caprolactone), poly(hydroxybutyrate), poly(lactide-co-glycolide), poly(lactide-co-caprolactone), and blends and copolymers thereof.
15. The method of claim 1 wherein step (d) utilizes lyophilization.
16. The method of claim 3 wherein the encapsulation is conducting using a process selected from the group consisting of interfacial polycondensation, spray drying, hot melt microencapsulation, and phase separation techniques.
17. (Amended) The method of claim 16 wherein the phase separation technique is selected from the group consisting of solvent extraction, solvent evaporation, and phase inversion.
18. The method of claim 17 wherein the mixture has a continuous phase containing the solvent and wherein the phase inversion technique comprises:  
  
introducing the mixture into a nonsolvent, wherein the volume ratio of solvent:nonsolvent is at least 1:40, to cause the spontaneous formation of a microencapsulated product, wherein the solvent and the nonsolvent are miscible.

U.S.S.N. 09/760,046

Filed: January 12, 2001

CLEAN VERSION OF AMENDMENTS PURSUANT TO 37 C.F.R. § 1.121(e)(1)(ii)

19. (Amended) The method of claim 18 wherein the solvent and non-solvent are slightly miscible.

20. The method of claim 18 wherein the volume ratio of solvent:nonsolvent is between 1:50 and 1:200.

21. The method of claim 18 wherein the macromolecular material is dissolved in the solvent at a concentration of less than 10% weight per volume and wherein the mixture has a viscosity of less than 3.5 cP.

22. The method of claim 20 wherein the concentration of the macromolecular material in the solvent is between 0.5 and 5% weight per volume.

23. (Amended) The method of claim 8 wherein freezing of the mixture is performed following addition of the agent to the solution at a rate effective to avoid denaturing of the protein.

C2 Sub E1  
24. (Amended) The method of claim 1 wherein the particles of agent are separated from the solid macromolecular material using a method comprising dissolving the macromolecular material in an effective amount of a solvent for the macromolecular material, wherein the solvent is a nonsolvent for the agent.

25. The method of claim 3 wherein the encapsulating material is a biocompatible polymer.

U.S.S.N. 09/760,046

Filed: January 12, 2001

CLEAN VERSION OF AMENDMENTS PURSUANT TO 37 C.F.R. § 1.121(c)(1)(ii)

26. The method of claim 25 wherein the biocompatible polymer is selected from polyesters, polyanhydrides, polystyrenes, poly(ortho)esters, copolymers thereof, and blends thereof.

*Rule 126 Sub 34*  
27. (New) The method of claim 1 wherein greater than 90% solid particles are less than 1  $\mu\text{m}$  in diameter.

ATL1 #563973 v1

ATL1 #563973 v1